



## DATASHEET – PRIMINGFOIL 6298-000-247-91 (UV-LACQUER)

The Likora priming foil is recoatable with all popular lacquer systems

### Components:

Basic : Melamine/urearesin-impregnated wood free paper with approx. 25% resin content  
Paperweight : 102gsm  
Print : Complete water based inks without any contingent of heavy metal  
Surface : UV-hardened lacquer with a recoatable surface

### End-product:

Final weight : approx. 110gsm  
Composition : 45-60% base paper, 20-25% resin content and approx. 10% of lacquer  
Tax-number : 48115900

### Advices for storage:

Condition : original packaged (unopened)  
Premises : dry, 13-22°C, 55-65% humidity  
Period of storage : max. 9 months

### Characteristics:

Formaldehyde category : E0,5  
Light fastness : WS 6 – light blue  
Scratch resistance : 500g (Hoffman) or 3,0N (Erichsen)  
Tape Pulls : No effect with „3M 810“, or „Scapa 2901“  
Surface tension :  $\geq 42\text{mN/m}$